

Product Data Sheet
Edition 5.13.2016
Sikaflex-1a

Sikaflex®-1a

One part polyurethane, elastomeric sealant/adhesive

SEALANT-WATERPROOFING & RESTORATION INSTITUTE

Issued to: Sika Corporation
Product: Sikaflex®-1A

C719: Pass Ext:+35% Comp:-35%

Substrate: Mortar, Aluminum, Glass
(mortar substrate primed with Sika Primer 429)

C661: Rating 40

Validation Date: 8/3/12 - 8/2/17

No. 0812-S11211 Copyright © 2012

SEALANT VALIDATION
www.swrionline.org

| | |
|----------------------------|---|
| Description | Sikaflex-1a is a premium-grade, high-performance, moisture-cured, 1-component, polyurethane-based, non-sag elastomeric sealant. Meets Federal specification TT-S-00230C, Type II, Class A. Meets ASTM C-920, Type S, Grade NS, Class 35, use T, NT, O, M, G, I; Canadian standard CAN/CGSB 19.13-M87. |
| Where to Use | <ul style="list-style-type: none"> ■ Designed for all types of joints where maximum depth of sealant will not exceed 1/2 in. ■ Excellent for small joints and fillets, windows, door frames, reglets, flashing, common roofing detail applications, and many construction adhesive applications. ■ Suitable for vertical and horizontal joints; readily placeable at 40°F. ■ Has many applications as an elastic adhesive between materials with dissimilar coefficients of expansion. ■ Submerged conditions, such as canal and reservoir joints. |
| Advantages | <ul style="list-style-type: none"> ■ Eliminates time, effort, and equipment for mixing, filling cartridges, pre-heating or thawing, and cleaning of equipment. ■ Fast tack-free and final cure times. ■ High elasticity - cures to a tough, durable, flexible consistency with exceptional cut and tear-resistance. ■ Stress relaxation. ■ Excellent adhesion - bonds to most construction materials without a primer. ■ Excellent resistance to aging, weathering. ■ Proven in tough climates around the world. ■ Odorless, non-staining. ■ Jet fuel resistant. ■ Certified to the NSF/ANSI Standard 61 for potable water. ■ Urethane-based; suggested by EPA for radon reduction. ■ Paintable with water-, oil- and rubber-based paints. ■ Capable of ±35% joint movement. |
| Chemical Resistance | Good resistance to water, diluted acids, and diluted alkalines. Consult Technical Service for specific data. |
| Packaging | 10.1 fl. oz. (300 mL), 20 fl. oz. (591 mL), 4.5 gal (17 L) in a 5 gal pail, 52 gal (197 L) in a 55 gal drum |

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

| | | |
|---|---|----------------------------------|
| Shelf Life | 10.1 fl. oz. cartridges | 12 months |
| | 20 fl. oz. uni-pac sausages | 12 months |
| | 5 gallon pail | 6 months |
| | 55 gallon drum | 6 months |
| Storage Conditions | Store at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using. | |
| VOC Content | 40 g/L | |
| Colors | White, colonial white, aluminum gray, limestone, black, dark bronze, capitol tan, stone and medium bronze. Special architectural colors on request. | |
| Application Temperature | 40° to 100°F. Sealant should be installed when joint is at mid-range of its anticipated movement. | |
| Service Range | -40° to 170°F | |
| Curing Rate | Tack-free time | 3 to 6 hours |
| | Tack-free to touch | 3 hours |
| | Final cure | 4 to 7 days |
| Tear Strength (ASTM D-624) | 55 lb./in. | |
| Shore A Hardness (ASTM C-661) | 21 day | 40±5 |
| Movement Capability (ASTM C-719) | +/- 35% | |
| Tensile Properties (ASTM D-412) | | |
| | 21 day | |
| | Tensile Stress | 175 psi (1.21 MPa) |
| | Elongation at Break | 550% |
| | Stress at 100% | 85 psi (0.59 MPa) |
| Adhesion in Peel (TT-S-00230C, ASTM C 794) | | |
| | Substrate | Peel Strength Adhesion Loss |
| | Concrete | 20 lb. 0% |
| | Aluminum | 20 lb. 0% |
| | Glass | 20 lb. 0% |
| Weathering Resistance | Excellent | |



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Coverage

| 10.1 oz Cartridge: Yield in Linear feet | | | | |
|---|-------|------|------|-----|
| Depth | 1/4" | 3/8" | 1/2" | |
| Width | 1/4" | 24.3 | | |
| | 3/8" | 16.2 | 10.8 | |
| | 1/2" | 12.1 | 8.1 | 6.1 |
| | 3/4" | 8.1 | 5.4 | 4.0 |
| | 1" | | | 3.0 |
| | 1.25" | | | 2.4 |
| | 1.5" | | | 2.0 |

| 20 oz Sausage: Yield in Linear feet | | | | |
|-------------------------------------|-------|------|------|------|
| Depth | 1/4" | 3/8" | 1/2" | |
| Width | 1/4" | 48.1 | | |
| | 3/8" | 32.1 | 21.4 | |
| | 1/2" | 24.1 | 16.0 | 12.0 |
| | 3/4" | 16.0 | 10.7 | 8.0 |
| | 1" | | | 6.0 |
| | 1.25" | | | 4.8 |
| | 1.5" | | | 4.0 |

| 1 gallon: Yield in Linear feet | | | | |
|--------------------------------|-------|-------|-------|------|
| Depth | 1/4" | 3/8" | 1/2" | |
| Width | 1/4" | 307.9 | | |
| | 3/8" | 205.3 | 136.8 | |
| | 1/2" | 153.9 | 102.6 | 77.0 |
| | 3/4" | 102.6 | 68.4 | 51.3 |
| | 1" | | | 38.5 |
| | 1.25" | | | 30.8 |
| | 1.5" | | | 25.7 |

How to Use

Surface Preparation

Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of oil and grease. Curing compound residues and any other foreign matter must be thoroughly removed. A roughened surface will also enhance bond. Install bond breaker tape or backer rod to prevent bond at base of joint.

Priming

Priming is not usually necessary. Most substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure.

Consult Sikaflex Primer Technical Data Sheet or Technical Service for additional information on priming.

Application

Recommended application temperatures: 40°-100°F.

For cold weather application, condition units at approximately 70°F; remove prior to using. For best performance, Sikaflex-1a should be gunned into joint when joint slot is at mid-point of its designed expansion and contraction. Place nozzle of gun into bottom of the joint and fill entire joint. Keep the nozzle in the sealant, continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping of sealant to eliminate entrapment of air.

Tooling and Finishing

Tool sealant to ensure full contact with joint walls and remove air entrapment. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio. For use in horizontal joints in traffic areas, the absolute minimum depth of the sealant is 1/2 in. and closed cell backer rod is recommended.

Removal

Use personal protective equipment (chemical resistant gloves/goggles/clothing). Without direct contact, remove spilled or excess product and placed in suitable sealed container. Dispose of excess product and container in accordance with applicable environmental regulations.

Over Painting

Allow 1-week cure at standard conditions when using Sikaflex-1a in total water immersion situations and prior to painting.

Limitations

- When overcoating with water, oil and rubber based paints, compatibility and adhesion testing is essential.
- Sealant should be allowed to cure for 7 days prior to overcoating.
- Avoid exposure to high levels of chlorine. (Maximum continuous level is 5 ppm of chlorine.)
- Maximum depth of sealant must not exceed 1/2 in.; minimum depth is 1/4 in.
- Maximum expansion and contraction should not exceed 25% of average joint width.
- Do not cure in the presence of curing silicone sealants.
- Avoid contact with alcohol and other solvent cleaners during cure.
- Do not apply when moisture-vapor-transmission condition exists from the substrate as this can cause bubbling within the sealant.
- Use opened cartridges and uni-pac sausages the same day.
- When applying sealant, avoid air-entrapment.
- Since system is moisture-cured, permit sufficient exposure to air.
- White color tends to yellow slightly when exposed to ultraviolet rays.
- Light colors can yellow if exposed to direct gas fired heating element.
- The ultimate performance of Sikaflex-1a depends on good joint design and proper application with joint surfaces properly prepared.
- The depth of sealant in horizontal joints subject to traffic is 1/2 in.
- Do not tool with detergent or soap solutions.
- Do not use in contact with bituminous/asphaltic materials.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks. Printed in Canada.

